



INTERNATIONAL
GEMOLOGICAL
INSTITUTE

ELECTRONIC COPY

LABORATORY GROWN DIAMOND REPORT

October 13, 2026

IGI Report Number

Description

Shape and Cutting Style

Measurements

LG846662408

LABORATORY GROWN DIAMOND

EMERALD CUT

6.97 X 4.73 X 3.04 MM

GRADING RESULTS

Carat Weight

Color Grade

Clarity Grade

1.07 CARAT

D

INTERNALLY FLAWLESS

ADDITIONAL GRADING INFORMATION

Polish

Symmetry

Fluorescence

EXCELLENT

EXCELLENT

NONE


Inscription(s)

Comments: As Grown - No indication of post-growth treatment.
This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process. Type II


 LG846662408

Report verification at igi.org

PROPORTIONS



CLARITY CHARACTERISTICS



KEY TO SYMBOLS

Red symbols indicate internal characteristics.

Green symbols indicate external characteristics.

COLOR

D

E

F

G

H

I

J

Faint

Very Light

Light

CLARITY

FL

IF

VVS¹⁻²

VS¹⁻²

SI¹⁻²

I¹⁻³

Flawless

Internally Flawless

Very Very Slightly Included

Very Slightly Included

Slightly Included

Included



© IGI 2020, International Gemological Institute

FD - 10 20

LABORATORY GROWN DIAMOND REPORT



October 13, 2026

IGI Report Number

Description

Shape and Cutting Style

Measurements

LG846662408

LABORATORY GROWN DIAMOND

EMERALD CUT

6.97 X 4.73 X 3.04 MM

GRADING RESULTS

Carat Weight

Color Grade

Clarity Grade

1.07 CARAT

D

INTERNALLY FLAWLESS

ADDITIONAL GRADING INFORMATION

Polish

Symmetry

Fluorescence

EXCELLENT

EXCELLENT

NONE

Inscription(s)

Comments: As Grown - No indication of post-growth treatment.
This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process. Type II

 LG846662408



IGI

October 13, 2026

IGI Report No LG846662408

EMERALD CUT

6.97 X 4.73 X 3.04 MM

Carat Weight

Color Grade

Clarity Grade

Depth

Table

Girdle

Slightly Thick

Long

Polish

Symmetry

Fluorescence

Inscription(s)

 LG846662408

Comments: As Grown - No indication of post-growth treatment.
This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process. Type II